



Berlin

| Number | Colour | Width mm | | | Light Properties | | | Solar Properties | | | Light Fastness | Gtot - value | FC - value |
|--------|---------------|----------|-----|------|------------------|-----|-----|------------------|-----|-----|----------------|--------------|------------|
| | | 89 | 127 | 2300 | R | T | A | R | T | A | | | |
| 1080 | white | ✓ | ✓ | ✓ | 66% | 27% | 7% | 58% | 29% | 13% | 5-6 | >0,45 | >0,80 |
| 2332 | cream | ✓ | ✓ | ✓ | 51% | 26% | 23% | 50% | 18% | 32% | 5-6 | >0,45 | >0,80 |
| 4191 | kiwi | ✓ | ✓ | ✓ | 19% | 18% | 63% | 18% | 26% | 56% | 5-6 | >0,45 | >0,80 |
| 9230 | rock | ✓ | ✓ | ✓ | 34% | 19% | 47% | 31% | 27% | 42% | 5-6 | >0,45 | >0,80 |
| 2421 | brown | ✓ | ✓ | ✓ | 28% | 18% | 54% | 27% | 20% | 53% | 5-6 | >0,45 | >0,80 |
| 4190 | spectra green | ✓ | ✓ | ✓ | 31% | 23% | 46% | 29% | 21% | 50% | 5-6 | >0,45 | >0,80 |
| 9239 | asphalt | ✓ | ✓ | ✓ | 18% | 18% | 64% | 15% | 25% | 60% | 5-6 | >0,45 | >0,80 |
| 8190 | mahogany | ✓ | ✓ | ✓ | 29% | 21% | 50% | 24% | 23% | 53% | 5-6 | >0,45 | >0,80 |
| 9238 | steel | ✓ | ✓ | ✓ | 8% | 5% | 87% | 7% | 7% | 86% | 5-6 | >0,45 | >0,80 |
| 2434 | nutwood | ✓ | ✓ | ✓ | 12% | 14% | 74% | 9% | 11% | 80% | 5-6 | >0,45 | >0,80 |
| 2379 | chocolate | ✓ | ✓ | ✓ | 8% | 7% | 85% | 6% | 7% | 87% | 5-6 | >0,45 | >0,80 |

All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Pleated/ Panel Track
 Colour Range 12
 Composition 100 % PES
 Width 89 / 127 / 2300 mm
 Cutting Process hot
 Processing Direction warp

Weight 220 g/m2
 Thickness 0,50 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for workstations



B semi-transparent



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc-value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.