

## Lisboa Opac

	Colour		Width mm			<b>Light Properties</b>			Solar Properties			Light	Gtot -	FC -
Number		89	127	2300	3000	R	Т	Α	R	Т	Α	Fastness val	value	value
1000	white-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2304	ivory-white	✓	✓	✓		84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9030	light grey-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9060	mouse grey-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2272	sand-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9092	anthracite-white	✓	✓	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
6025	yellow-white	✓	✓	✓		84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
4125	light green-white	✓	✓	✓		84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
5053	blue-white blue-white	✓	✓	✓		84%	0%	16%	71%	0%	29%	6-7	0,34	0,58

Usable for Colour Range Composition Width **Cutting Process**  Roller / Vertical / Panel Track

100 % PES

Processing Direction warp & weft

89 / 127 / 2300 / 3000 mm

Weight 420 g/m<sup>2</sup> Thickness 0,50 mm Moisture proofed yes PVC free yes yes

retardant

DIN 4102, B1 NF P 92-503-507,M1 BS 5867 part 2 UNI 8456-UNI 9174 C1 EN 13773 class 1 NFPA 701- USA



suitable for workstations



D black-out



R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.