

Lisboa

Number	Colour	89	Width mm 89 127 2300 3000			Light Properties R T A		Solar Properties R T A			Light Fastness	Gtot - value	FC - value	
1021	white	~	~	~	~	84 %	15%	1%	72%	16%	12%	6-7	0,34	0,58
2103	beige	~	~	~	~	79%	14 %	7%	7 0%	16%	14 %	6-7	0,34	0,58
9030	grey	~	~	~	~	55%	5%	40 %	52%	7%	41 %	6-7	0,40	0,68
9060	mouse grey	~	~	✓	~	30%	0%	7 0%	29%	2%	69%	6-7	0,4 7	0,80
2272	sand	~	~	✓	~	69%	9%	22%	6 4%	13%	23%	6-7	0,36	0,61
9163	black	✓	~	✓		4 %	2%	94 %	3%	8%	89%	6-7	0,56	0,95
2071	cream	~	✓	✓		7 0%	12%	18%	63%	15%	22%	6-7	0,3 7	0,63
4125	light green	√	~	✓		68%	9%	23%	60%	13%	27%	6-7	0,38	0,64
5049	blue	~	✓	~		31%	1%	68%	41 %	6%	53%	6-7	0,44	0, 7 5

Usable for Colour Range 18 Composition Width **Cutting Process** Processing Direction

Roller / Vertical / Panel Track 100 % PES 89/127/2300/3000mm cold warp & weft

Weight 220 g/m² Thickness 0,30 mm yes yes yes

DIN 4102, B1 NF P 92-503-507,M1 BS 5867 part 2 NFPA 701- USA Flame



4

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g . Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. + All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.

retardant

Moisture proofed PVC free OekoTex