



Luna Opac

Number	Colour	Width mm		Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
		2000	3000	R	T	A	R	T	A			
1039	nature white	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9191	light grey	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2326	bleached sand	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
4166	pesto	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9193	silver	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
2393	cinder	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58
9192	black	✓	✓	84%	0%	16%	71%	0%	29%	6-7	0,34	0,58


All printed colours and textures only. No color orientation and all are in reference pattern.

Usable for Roller / Panel Track
 Colour Range 12
 Composition 100 % PES
 Width 2000 / 3000 mm
 Cutting Process coil
 Processing Direction warp & weft

Weight 360 g/m²
 Thickness 0,55 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for Workstations



D black-out



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.