



LUNA

Number	Colour	89	Width mm			Light Properties			Solar Properties			Light Fastness	Gtot - value	FC - value
			127	2000	3000	R	T	A	R	T	A			
1039	nature white			✓	✓	77%	15%	8%	75%	18%	7%	6-7	0,33	0,56
2326	bleached sand			✓		54%	17%	29%	50%	22%	28%	6-7	0,41	0,69
6116	soft yellow			✓		55%	20%	25%	48%	23%	29%	6-7	0,42	0,71
9191	light grey			✓	✓	54%	17%	29%	50%	22%	28%	6-7	0,41	0,69
8165	red			✓	✓	25%	9%	66%	24%	13%	63%	6-7	0,49	0,83
9193	silver			✓	✓	27%	9%	64%	26%	13%	61%	6-7	0,49	0,83
5203	sky blue			✓		58%	14%	28%	55%	16%	29%	6-7	0,39	0,66
2393	cinder			✓		31%	8%	61%	28%	13%	59%	6-7	0,48	0,81
4166	pesto			✓	✓	8%	5%	87%	8%	11%	81%	6-7	0,54	0,92
4165	tropical green			✓		30%	8%	62%	27%	13%	60%	6-7	0,48	0,81
9192	black			✓	✓	4%	1%	95%	3%	4%	93%	6-7	0,56	0,95


All printed colours and textures only provide orientation and are not reference pattern.

Usable for Roller / Vertical / Panel Track
 Colour Range 12 / 24
 Composition 100 % PES
 Width 89 / 127 / 2000 / 3000 mm
 Cutting Process cold
 Processing Direction warp & weft

Weight 210 g/m²
 Thickness 0,45 mm
 Moisture proofed yes
 PVC free yes
 Halogen free yes
 OekoTex yes



suitable for Workstations



B semi-transparent



by Gerhard van Clewe GmbH & Co.KG



Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption • All light & solar properties have been tested internally or externally. • Gtot: measure total solar energy that passes through the glazing system and the fabric • Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g • Gtot and Fc-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. • All technical properties are subjected to production-related deviations. All fabrics are in line with the REACH regulation.