



Paris

Number			Width mm			Light Properties			Solar Properties			Light	Gtot -	FC -
	Colour	89	127	2000	3000	R	T	Α	R	Т	Α	Fastness	value	value
1078	white			✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58
9165	grey			✓	✓	52%	14%	34%	49%	16%	35%	6-7	0,41	0,69
2103	beige			✓	✓	64%	19%	17%	60%	17%	23%	6-7	0,38	0,64
9199	flint grey	N TO A TO	7	✓	✓	19%	9%	72%	17%	11%	72%	6-7	0,51	0,86
9198	steel grey	1010101		✓	✓	8%	5%	87%	7%	7%	86%	6-7	0,55	0,93
2326	bleached sand			✓	✓	59%	28%	13%	56%	24%	20%	6-7	0,39	0,66
9092	black			✓	✓	1%	2%	97%	1%	5%	94%	6-7	0,57	0,97
5206	hawaiian ocean	202020		✓		29%	14%	57%	27%	15%	58%	6-7	0,48	0,81
5207	imperial blue	NA CONTRACTOR OF THE PARTY OF T		✓		22%	11%	67%	19%	13%	68%	6-7	0,51	0,86
6119	spectra yellow			✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58
8168	baton rougue			✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58
4170	jasmin green	THE PARTY OF THE P		✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58
4171	fern green			✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58
6117	french vanille			✓	✓	77%	20%	3%	71%	23%	6%	6-7	0,34	0,58

Usable for Roller / Vertical / Panel Track
Colour Range 30

Composition 100 % PES Width 89 / 127 / 2000 / 3000 mm

Cutting Process cold Processing Direction warp & weft Weight 190 g/m²
Thickness 0,30 mm
Moisture proofed yes
PVC free yes
Halogen free yes
OekoTex yes













Standard 100 by Oeko-Tex®

R = Reflection, T = Transmission, A = Absorption · All light & solar properties have been tested internally or externally. · Gtot: measure total solar energy that passes through the glazing system and the fabric · Fc value: Relation between the total energy transmittance of glazing combined with the sun shading device gtot in combination with total energy transmittance of glazing g · Gtot and FC-value are calculated on the basis of a glass with an Ug-value of 1,2 and g-value of 0,59 according to DIN EN 14501 glass C. · All technical properties are subjected to production-related deviations. All fabrics are in line with the REACh regulation.