

Blockout PE Ruka







POLYESTER OF = 0%

Technical specifications

TECHNICAL SPECIFICATION		UNITY STA		STANDARD	RESULT		
composition				Polyester 66% - PUR 34%			
openness factor		%		NBN EN 410	0%		
weight		g/m²		NF EN 12127	310		
thickness		mm		ISO 2286-3	0,25		
colour fastness to artificial light			front	ISO 105 B02	6		
colour lastriess to artificial light			back	ISO 103 B02	>7		
tear strength	original	daN	warp	ISO 4674-1 method 2	1,65		
tear strongth	Original	GGIV	weft	100 4014 1 Medica 2	3,1		
elongation up to break	original	%	warp	ISO 1421	26,5		
olongation up to broak	Original	70	weft	100 1421	30		
breaking strength	original	daN/5 cm	warp	ISO 1421	125		
broading deoriger	ong. idi	Gara, O Gill	weft	100 1 12 1	165		
elongation up to break	after colour fastness to artificial light	%	warp	ISO 1421	23,5		
olongation up to broat		/*	weft	NOO T NET	30		
breaking strength	after colour fastness to artificial light	daN/5 cm	warp	ISO 1421	120		
			weft		160		
tear strength	after climatic chamber -30°C	daN	warp	ISO 4674-1 method 2	1,5		
			weft		2,9		
elongation up to break	after climatic chamber -30°C	%	warp	ISO 1421	29,5 33		
			weft		135		
breaking strength	after climatic chamber -30°C	daN/5 cm	warp weft	ISO 1421	170		
			warp		1,65		
tear strength	after climatic chamber +70°C	daN	waip	SO 4674-1 method 2	3,2		
			warp		28		
elongation up to break	after climatic chamber +70°C	%	weft	ISO 1421	28.5		
			warp		130		
breaking strength	after climatic chamber +70°C	daN/5 cm	weft	ISO 1421	160		
	Europe			UNE-EN 13501-1:2007	B-s2,d0		
fire classification	Germany	DIN 4102	B2				
	Spain						
roll length			30 m	·	Clase 1		
cleaning	with soapy water						
confection	by	by heat, high frequency or ultrasonic welding					

Blockout PE Ruka 015015 linen

















4 COPACO BLOCK COPACO BLOCKOUT PE RUKA 5



Blockout PE Ruka







POLYESTER OF = 0%

Colours & references






Blockout PE Ruka 002002 white

Blockout PE Ruka 015015 linen

Blockout PE Ruka 008008 sand





Blockout PE Ruka 007007 pearl grey

Blockout PE Ruka 010010 charcoal

Blockout PE Ruka	260 cm
002002 white	•
015015 linen	•
008008 sand	
007007 pearl grey	
010010 charcoal	

Solar energetic properties

							SOLAR ENERGETIC PROPERTIES						
Blockout PE Ruka								FABRIC + GLAZING			3	VISUAL	
	F 64	EN 44504				FABRIC			INTE	RIOR			ERTIES
European Standard EN 14501 Calculation G-value according to EN 13363-1 version 7.0			FABRIC		total s	G-fac olar enerç	ctor = gy transm	ittance	FROFERIES				
references	colours	front	back	7	As = Solar Absorptance %	Rs = Solar Reflectance %	Is = Solar Transmittance %	Glazing A - Gv = 0,85 - U = 5,8	Glazing B - Gv = 0,76 - U = 2,9	Glazing C - Gv = 0,59 - U = 1,2	Glazing D - Gv = 0,32 - U = 1,1	Tv = Visible Light Transmittance %	Tuv = UV Transmittance %
		HOIK	94.000	front	31,0	69,0	0,0	0,31	0,34	0,34	0,25	0,0	0,0
002002	white		District the second	back	54,3	45,7	0,0	0,45	0,46	0,42	0,27	0,0	0,0
015015	linen		25.000	front	37,7	62,3	0,0	0,35	0,37	0,36	0,25	0,0	0,0
010010	linen		1000	back	51,2	48,8	0,0	0,43	0,44	0,41	0,26	0,0	0,0
008008	sand			front	44,6	55,4	0,0	0,39	0,41	0,39	0,26	0,0	0,0
000000	Guila		000000	back	51,8	48,2	0,0	0,43	0,45	0,41	0,26	0,0	0,0
007007	pearl grey			front	55,5	44,5	0,0	0,45	0,47	0,42	0,27	0,0	0,0
00,007	pour groy		100000	back	49,6	50,4	0,0	0,42	0,44	0,40	0,26	0,0	0,0
010010	charcoal			front	95,5	4,5	0,0	0,69	0,67	0,55	0,30	0,0	0,0
0.00.0	0.10.000		0.00	back	50,4	49,6	0,0	0,42	0,44	0,41	0,26	0,0	0,0

GLAZING A = clear single glazing 4 mm	Gv = 0,85
GLAZING B = clear double glazing (4/12/4), space filled with air	Gv = 0,76
GLAZING C = double glazing (4/16/4), with a low emissivity coating in position 3, space filled with argon	Gv = 0,59
GLAZING D = reflective double glazing (4/16/4), with a low emissivity coating in position 2, space filled with argon	Gv = 0,32


6 COPACO BLOCK COPACO BLOCKOUT PE RUKA 7

Working of a sunscreen



Sunscreen = protection against sunrays

Sunscreen means protection against the sunrays, so the function is the protection against light and heat, which is expressed in several properties.



Rs	Solar reflectance					
As	Solar absorptance					
Ts	Solar transmittance					
Te,n-dif	Diffuse solar transmittance					
Te,n-n	Normal solar transmittance					

Classes indicate effect of a sunscreen


Based on certain properties, the screen can be split up in classes, from 0 to 4. Those classes are used, starting from the norm EN 14501, to indicate the effect of a certain sunscreen.

influence on thermal and visual comfort						
Class 0	very little effect					
Class 1	little effect					
Class 2	moderate effect					
Class 3	good effect					
Class 4	very good effect					

Visual properties

Openness factor

The openness of a screen is indicated by the openness factor = **OF.**The openness coefficient is the relative area of the openings in the fabric seen under a given incidence. The openness factor is seen under a normal incidence.



The sunrays are subdivided in: Visible light, UV-light and IR-light.

Visible light (55% of the sun-energy) is that part for which our eyes are most sensitive. How larger the light intensity, how more detrimental for our eyes.

The factor Visible Light Transmittance = Tv, is the ratio of visible light that will be transmitted. How lower this factor can be kept, how better for the eyes.

UV-light (3% of the sun-energy) is the part of radiation which is detrimental for our health. This factor is indicated by the UV Transmittance = **Tuv.** This is the quantity UV-light transmitted by the sunscreen.

IR-light is invisible. This is however 42% of the sun-energy. These rays care for the reheating of solid substances and gases.

Influence of colours

The choice of the colour has direct influence on the criteria which justify the use of sunscreen protection:

- Protection against visible light, expressed by the factor Tv.
- Protection against sun-energy, expressed by the G value.
- Protection against secondary heat, expressed by the factor Qi.
- · Protection against UV-light, expressed by the factor Tuv.

Visual properties: classes

Glare control

The capacity of the solar protection device to control the luminance level of openings and to reduce the luminance contrasts between different zones within the field.

Tunn	Tv,n-dif					
Tv,n-n	Tv,n-dif < 0,02	0,02 ≤ Tv,n-dif < 0,04	0,04 ≤ Tv,n-dif < 0,08	Tv,n-dif ≥ 0,08		
Tv,n-n > 0,10	0	0	0	0		
0,05 < Tv,n-n ≤ 0,10	1	1	0	0		
T v,n-n ≤ 0,05	3	2	1	1		
Tv,n-n = 0,00	4	3	2	2		

Privacy at night

Night privacy is the capacity of an internal or external blind or a shutter in the fully extended position or fully extended and closed position to protect persons, at night in normal light conditions from external view. External views means the ability of an external observer located 5m from the fully extended and closed product, to distinguish a person or object standing 1m behind the protection device in the room.

Tv.n-n		Tv,n-dif					
LV,TI=TI		0 < Tv,n-dif ≤ 0,04	0,04 < Tv,n-dif ≤ 0,15	Tv,n-dif > 0,15			
Tv,n-n > 0,10		0	0	0			
0,05 < Tv,n-n ≤ 0	,10	1	1	1			
Tv,n-n ≤ 0,05		2	2	2			
Tv,n-n = 0,00		4	3	2			

Visual contact with the outside

Visual contact with the outside is the capacity of the solar protection device to allow an exterior view when it is fully extended. This function is affected by different light conditions during the day.

Tv.n-n	Tv,n-dif					
LV,H-H	0 < Tv,n-dif ≤ 0,04	0,04 < Tv,n-dif ≤ 0,15	Tv,n-dif > 0,15			
Tv,n-n > 0,10	4	3	2			
0,05 < Tv,n-n ≤ 0,10	3	2	1			
Tv,n-n ≤ 0,05	2	1	0			
Tv,n-n = 0,00	0	0	0			

Daylight utilisation

Daylight utilisation is characterised by:

- the capacity of the solar protection device to reduce the time period during the artificial light is required.
- the capacity of the solar protection device to optimise the daylight which is available.

CLASS	0	1	2	3	4
Tv,dif-h	Tv,dif-h < 0,02	0,02 ≤ Tv,dif-h < 0,10	0,10 ≤ Tv,dif-h < 0,25	0,25 ≤ Tv,dif-h < 0,40	Tv,dif-h ≥ 0,40

COPACO BLOCK COPACO BLOCKOUT PE RUKA


Working of a sunscreen




Thermal comfort

Fabric

Energy radiated by the sun, will be split up in 3 factors:



The G-factor



Rs	Solar reflectance
As	Solar absorptance
Te	Direct solar transmittance
Qi	Secondary heat transfer factor
G	G-factor = total solar energy transmittance

Sunscreens are always used in combination with a glazing. These together will prevent a large quantity of energy, sent by the sun to the earth, which is indicated by the: Total Solar Energy Transmittance, or **G-factor**.

The ${\bf G}$ value is the ratio between the total solar energy transmitted into a room through a window and the incident solar energy on the window. The ${\bf Gtot}$ is the solar factor of the combination of glazing and solar protection device.

The Gv is the solar factor of the glazing alone.

The shading coefficient is defined as the ratio of the solar factor of the combined glazing and solar protection device **Gtot** to that of the glazing alone **Gv.**

The total solar energy transmitted through a window consists of

1) Radiation: measured by the solar transmittance: Te,tot

2) Heat: measured by the secondary heat transfer: Qi


G = Te,tot + Qi

The factor **Te,tot**, is the quantity of energy, which will pass the combination solar protection device and window.

The factor **Qi** is the quantity of heat which is released by the absorption of energy in the sunscreen protection system = combination sunscreen + glazing.

The **G-factor** is the most important factor to explain the efficiency of a combination sunscreen + glazing, as protection against the energy of the sun. The **G-factor** divided into his components explains the difference in efficiency between exterior and interior sunscreen.

G = Te,tot + Qi



The direct solar transmittance \mathbf{Te} , \mathbf{tot} is the same for interior and exterior use of sunscreens.

The secondary heat factor **Qi** for interior sunscreen is bigger then for exterior sunscreen. For interior use, the heat, produced by the absorption of energy, will be transmitted to the room inside. By exterior use, the heat will be transmitted to the outside, without any inconvenience at the inside.

Also the colour of the sunscreen has an influence on the **G-factor**. Dark colours will absorb a lot of sun energy and will transmit this to heat. If the screen is used for exterior, heat will have no influence inside the room, contrary to a screen used for interior. This is why a darker screen is ideal for exterior use and a lighter screen for interior use.





Thermal comfort: classes

Total Solar energy Transmittance = G-factor

CLASS	0	1	2	3	4
Gtot	Gtot ≥ 0,50	0,35 ≤ Gtot < 0,50	0,15 ≤ Gtot < 0,35	0,10 ≤ Gtot < 0,15	Gtot < 0,10

Secondary Heat transfer = Qi

CLASS	0	1	2	3	4
Qi	Qi ≥ 0,30	0,20 ≤ Qi < 0,30	0,10 ≤ Qi < 0,20	0,03 ≤ Qi < 0,10	Qi < 0,03

Normal Solar transmittance = protection against direct transmission

The ability of a solar protection device to protect persons and surroundings from direct irradiation is measured by the direct/direct solar transmittance of the device in combination with the glazing. Te,n-n is used as measure for this property.

10 COPACO BLOCK COPACO BLOCKOUT PE RUKA 11