



Serge 600 BO Lunar



GLASSFIBRE

OF = 0%

Technical specifications

TECHNICAL SPECIFICATION		UNITY	STANDARD	RESULT
composition			Fibreglass 33 % - PVC 47 % - PVC laminate 20 %	
openness factor		%	NBN EN 410	0%
weight		g/m ²	NF EN 12127	678
thickness		mm	ISO 2286-3	0,73
density		yarn/cm	warp	18,0
			weft	14,0
colour fastness to artificial weathering			ISO 105 B04	>7
tear strength	original	daN	warp	8,5
			weft	9,0
elongation up to break	original	%	warp	6,4
			weft	7,3
breaking strength	original	daN/5 cm	warp	224,2
			weft	176,6
elongation up to break	after colour fastness to artificial weathering	%	warp	6,5
			weft	7,0
breaking strength	after colour fastness to artificial weathering	daN	warp	214,2
			weft	168,0
tear strength	after climatic chamber -30°C	daN	warp	8,4
			weft	9,3
elongation up to break	after climatic chamber -30°C	%	warp	6,2
			weft	6,9
breaking strength	after climatic chamber -30°C	daN/5 cm	warp	222,4
			weft	162,6
tear strength	after climatic chamber +70°C	daN	warp	8,8
			weft	9,3
elongation up to break	after climatic chamber +70°C	%	warp	6,4
			weft	6,7
breaking strength	after climatic chamber +70°C	daN/5 cm	warp	213,9
			weft	161,6
air permeability		l/m ² .s	ISO 9237	0,01m ³ /s
fire classification	Europe		UNE-EN 13501-1:2007	
	France		NF P92-503	M1
	Italy		UNI 9177	Classe 1
	Germany		DIN 4102	B1
	UK		BS 5867	
	USA		NFPA 701	
roll length	30 m			
cleaning	with soapy water			
confection	by heat, high frequency or ultrasonic welding			

These properties are given as indicative and don't have any contractual value

Recommendation: to be used in sunscreensystems with Zipscreens.






Serge 600 BO Lunar



GLASSFIBRE

OF = 0%

Colours & references



Serge 600 BO Lunar 002002 white | white



Serge 600 BO Lunar 002007 white | pearl grey




Serge 600 BO Lunar 007007 pearl grey | pearl grey



Serge 600 BO Lunar 001002 grey | white



Serge 600 BO Lunar 033001 oyster shell



Serge 600 BO Lunar 001001 grey | grey



Serge 600 BO Lunar 001010 grey | charcoal



Serge 600 BO Lunar 010010 charcoal | charcoal

Serge 600 BO Lunar	210 cm
002002 white white	•
002007 white pearl grey	•
007007 pearl grey pearl grey	•
001002 grey white	•
033001 oyster shell	•
001001 grey grey	•
001010 grey charcoal	•
010010 charcoal charcoal	•

Solar energetic properties

Serge 600 BO Lunar		SOLAR ENERGETIC PROPERTIES												VISUAL PROPERTIES		
		FABRIC			FABRIC + GLAZING											
					EXTERIOR				INTERIOR							
G-factor = total solar energy transmittance																
references	colours			As = Solar Absorbance %	Rs = Solar Reflectance %	Ts = Solar Transmittance %	G-factor = total solar energy transmittance								Tv = Visible Light Transmittance %	Tuv = UV Transmittance %
							front	back	front	back	front	back	front	back		
002002	white white	front		31,2	68,8	0,0	0,04	0,03	0,02	0,29	0,33	0,34	0,24	0,0	0,0	
		back		66,3	33,7	0,0	0,09	0,07	0,03	0,03	0,47	0,50	0,45	0,27	0,0	0,0
002007	white pearl grey	front		52,2	47,8	0,0	0,07	0,05	0,03	0,03	0,40	0,43	0,40	0,26	0,0	0,0
		back		66,8	33,2	0,0	0,09	0,07	0,04	0,03	0,47	0,50	0,45	0,27	0,0	0,0
007007	pearl grey pearl grey	front		64,5	35,5	0,0	0,09	0,06	0,03	0,03	0,46	0,49	0,44	0,27	0,0	0,0
		back		66,0	34,0	0,0	0,09	0,06	0,03	0,03	0,47	0,49	0,45	0,27	0,0	0,0
001002	grey white	front		59,7	40,3	0,0	0,08	0,06	0,03	0,03	0,44	0,46	0,43	0,27	0,0	0,0
		back		66,3	33,7	0,0	0,09	0,07	0,03	0,03	0,47	0,50	0,45	0,27	0,0	0,0
033001	oyster shell	front		81,8	18,2	0,0	0,12	0,08	0,04	0,04	0,55	0,57	0,50	0,29	0,0	0,0
		back		66,6	33,4	0,0	0,09	0,07	0,04	0,03	0,47	0,50	0,45	0,27	0,0	0,0
001001	grey grey	front		82,8	17,2	0,0	0,12	0,08	0,04	0,04	0,55	0,57	0,50	0,29	0,0	0,0
		back		66,9	33,1	0,0	0,09	0,07	0,04	0,03	0,47	0,50	0,45	0,27	0,0	0,0
001010	grey charcoal	front		89,0	11,0	0,0	0,13	0,09	0,05	0,04	0,59	0,60	0,52	0,29	0,0	0,0
		back		66,3	33,7	0,0	0,09	0,07	0,04	0,03	0,47	0,50	0,45	0,27	0,0	0,0
010010	charcoal charcoal	front		93,8	6,2	0,0	0,13	0,09	0,05	0,05	0,61	0,63	0,53	0,30	0,0	0,0
		back		66,6	33,4	0,0	0,09	0,07	0,04	0,03	0,47	0,50	0,45	0,27	0,0	0,0


GLAZING A = clear single glazing 4 mm	Gv = 0,85
GLAZING B = clear double glazing (4/12/4), space filled with air	Gv = 0,76
GLAZING C = double glazing (4/16/4), with a low emissivity coating in position 3, space filled with argon	Gv = 0,59
GLAZING D = reflective double glazing (4/16/4), with a low emissivity coating in position 2, space filled with argon	Gv = 0,32

Working of a sunscreen



Sunscreen = protection against sunrays

Sunscreen means protection against the sunrays, so the function is the protection against light and heat, which is expressed in several properties.



Rs	Solar reflectance
As	Solar absorptance
Ts	Solar transmittance
Te,n-dif	Diffuse solar transmittance
Te,n-n	Normal solar transmittance

Classes indicate effect of a sunscreen


Based on certain properties, the screen can be split up in classes, from 0 to 4. Those classes are used, starting from the norm EN 14501, to indicate the effect of a certain sunscreen.

influence on thermal and visual comfort	
Class 0	very little effect
Class 1	little effect
Class 2	moderate effect
Class 3	good effect
Class 4	very good effect

Visual properties

Openness factor

The openness of a screen is indicated by the openness factor = **OF**. The openness coefficient is the relative area of the openings in the fabric seen under a given incidence. The openness factor is seen under a normal incidence.



The sunrays are subdivided in: **Visible light**, **UV-light** and **IR-light**.

Visible light (55% of the sun-energy) is that part for which our eyes are most sensitive. How larger the light intensity, how more detrimental for our eyes.

The factor Visible Light Transmittance = **Tv**, is the ratio of visible light that will be transmitted. How lower this factor can be kept, how better for the eyes.

UV-light (3% of the sun-energy) is the part of radiation which is detrimental for our health. This factor is indicated by the UV Transmittance = **Tuv**. This is the quantity UV-light transmitted by the sunscreen.

IR-light is invisible. This is however 42% of the sun-energy. These rays care for the reheating of solid substances and gases.

Influence of colours

The choice of the colour has direct influence on the criteria which justify the use of sunscreen protection:

- Protection against visible light, expressed by the factor **Tv**.
- Protection against sun-energy, expressed by the **G** value.
- Protection against secondary heat, expressed by the factor **Qi**.
- Protection against UV-light, expressed by the factor **Tuv**.

Visual properties: classes

Glare control

The capacity of the solar protection device to control the luminance level of openings and to reduce the luminance contrasts between different zones within the field.

Tv,n-n	Tv,n-dif			
	Tv,n-dif < 0,02	0,02 ≤ Tv,n-dif < 0,04	0,04 ≤ Tv,n-dif < 0,08	Tv,n-dif ≥ 0,08
Tv,n-n > 0,10	0	0	0	0
0,05 < Tv,n-n ≤ 0,10	1	1	0	0
Tv,n-n ≤ 0,05	3	2	1	1
Tv,n-n = 0,00	4	3	2	2

Privacy at night

Night privacy is the capacity of an internal or external blind or a shutter in the fully extended position or fully extended and closed position to protect persons, at night in normal light conditions from external view. External views means the ability of an external observer located 5m from the fully extended and closed product, to distinguish a person or object standing 1m behind the protection device in the room.

Tv,n-n	Tv,n-dif		
	0 < Tv,n-dif ≤ 0,04	0,04 < Tv,n-dif ≤ 0,15	Tv,n-dif > 0,15
Tv,n-n > 0,10	0	0	0
0,05 < Tv,n-n ≤ 0,10	1	1	1
Tv,n-n ≤ 0,05	2	2	2
Tv,n-n = 0,00	4	3	2

Visual contact with the outside

Visual contact with the outside is the capacity of the solar protection device to allow an exterior view when it is fully extended. This function is affected by different light conditions during the day.

Tv,n-n	Tv,n-dif		
	0 < Tv,n-dif ≤ 0,04	0,04 < Tv,n-dif ≤ 0,15	Tv,n-dif > 0,15
Tv,n-n > 0,10	4	3	2
0,05 < Tv,n-n ≤ 0,10	3	2	1
Tv,n-n ≤ 0,05	2	1	0
Tv,n-n = 0,00	0	0	0

Daylight utilisation

Daylight utilisation is characterised by:

- the capacity of the solar protection device to reduce the time period during the artificial light is required.
- the capacity of the solar protection device to optimise the daylight which is available.

CLASS	0	1	2	3	4
Tv,dif-h	Tv,dif-h < 0,02	0,02 ≤ Tv,dif-h < 0,10	0,10 ≤ Tv,dif-h < 0,25	0,25 ≤ Tv,dif-h < 0,40	Tv,dif-h ≥ 0,40

Working of a sunscreen




Thermal comfort

Fabric

Energy radiated by the sun, will be split up in 3 factors:

factor 1:	factor 2:	factor 3:
<p>As = Solar absorptance is the ratio of the absorbed flux to the incident flux.</p>	<p>Rs = Solar reflectance is the fraction of the incident solar radiation that is directly reflected by the component.</p>	<p>Ts = Solar transmittance is the sum of the (normal) direct solar transmittance and the diffuse solar transmittance. This is the fraction of the total transmitted energy to the total incident solar radiation.</p>
These 3 factors together are always 100%		

The G-factor



Rs	Solar reflectance
As	Solar absorptance
Te	Direct solar transmittance
Qi	Secondary heat transfer factor
G	G-factor = total solar energy transmittance

Sunscreens are always used in combination with a glazing. These together will prevent a large quantity of energy, sent by the sun to the earth, which is indicated by the: Total Solar Energy Transmittance, or **G-factor**.

The **G** value is the ratio between the total solar energy transmitted into a room through a window and the incident energy on the window. The **Gtot** is the solar factor of the combination of glazing and solar protection device.

The **Gv** is the solar factor of the glazing alone. The shading coefficient is defined as the ratio of the solar factor of the combined glazing and solar protection device **Gtot** to that of the glazing alone **Gv**.

The total solar energy transmitted through a window consists of two parts:

- 1) Radiation: measured by the solar transmittance: **Te,tot**
- 2) Heat: measured by the secondary heat transfer: **Qi**


$$G = Te,tot + Qi$$

The factor **Te,tot**, is the quantity of energy, which will pass the combination solar protection device and window. The factor **Qi** is the quantity of heat which is released by the absorption of energy in the sunscreen protection system = combination sunscreen + glazing.


The **G-factor** is the most important factor to explain the efficiency of a combination sunscreen + glazing, as protection against the energy of the sun. The **G-factor** divided into his components explains the difference in efficiency between exterior and interior sunscreen.

$$G = Te,tot + Qi$$

exterior sunscreen



interior sunscreen



The direct solar transmittance **Te,tot** is the same for interior and exterior use of sunscreens.

The secondary heat factor **Qi** for interior sunscreen is bigger than for exterior sunscreen. For interior use, the heat, produced by the absorption of energy, will be transmitted to the room inside. By exterior use, the heat will be transmitted to the outside, without any inconvenience at the inside.

Also the colour of the sunscreen has an influence on the **G-factor**. Dark colours will absorb a lot of sun energy and will transmit this to heat. If the screen is used for exterior, heat will have no influence inside the room, contrary to a screen used for interior. This is why a darker screen is ideal for exterior use and a lighter screen for interior use.

Thermal comfort: classes

Total Solar energy Transmittance = G-factor

CLASS	0	1	2	3	4
Gtot	$Gtot \geq 0,50$	$0,35 \leq Gtot < 0,50$	$0,15 \leq Gtot < 0,35$	$0,10 \leq Gtot < 0,15$	$Gtot < 0,10$

Secondary Heat transfer = Qi

CLASS	0	1	2	3	4
Qi	$Qi \geq 0,30$	$0,20 \leq Qi < 0,30$	$0,10 \leq Qi < 0,20$	$0,03 \leq Qi < 0,10$	$Qi < 0,03$

Normal Solar transmittance = protection against direct transmission

The ability of a solar protection device to protect persons and surroundings from direct irradiation is measured by the direct/direct solar transmittance of the device in combination with the glazing. **Te,n-n** is used as measure for this property.